# **TECHNICAL DATA SHEET – OCTOBER 2017**

Woodworking Adhesive

## **RAKOLL XL3 HV LOT**

Page 1 of 2 Version 2 17/10/2017

### **Characteristics:**

RAKOLL XL3 HV LOT is a high performance, one-part cross-linking PVA wood glue which when cured gives strong bonds in general carpentry, door pressing and veneering applications.

Bonds made with RAKOLL XL3 HV LOT exhibit good heat and water resistance and will conform to EN 204 – Group D3. It is therefore ideal for use in high humidity areas such as bathrooms and laundries.

RAKOLL XL3 HV LOT is a long open time product particularly suited to cold press operations

Appearance	White creamy liquid
Dry Film	Tough and hard yet flexible
Viscosity	12,000 – 14,000 cPs
Total Solids Content	41 - 44 %
Specific Gravity	1.06 g/ml
рН	3 - 5

### **Application Information**

RAKOLL XL3 HV LOT is designed to be used by squeeze bottle or roller. Dilution is not recommended. Ensure substrates are free form oils dirt or grease.

### Woodworking

- Timber moisture content should be between 10% and 12%.
- Ambient and timber temperatures should be above 15°C. Best results are obtained when operating in the temperature range of 18-23°C.

- Adhesive should be applied as a thin, even coating to one surface only. Apply enough adhesive to ensure the glue line is fully covered and wet-out when surfaces are pressed together.
- Parts should be combined, while the adhesive is wet, using good even pressure; 200-900 kPa
- (30 to 130 psi) is recommended.
- Parts should be clamped for 3 to 4 hours and will reach full strength in 24 to 48 hours, depending on the moisture content of the timber, ambient temperature and humidity.

### **Door Pressing and Veneering**

- Application rate should be tested on each species of veneer. It will vary depending upon absorption rates but an indicative norm to achieve good bonds is 190-240 gsm.
- Open time should not exceed 15-20 minutes.
- Assembly time should not exceed 20 minutes.
- Best results are obtained by a pressing platen temperature of 90-105°C for approximately
- 45-60 seconds using a pressure of 400 600 kPa (4 – 6 bar).

### Our Focus is Clear. Perfecting Adhesives.

IMPORTANT: Information, specifications, procedures and recommendations provided ("information") are based on our experience and we believe this to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

NOTE TO USER: by ordering/receiving product you accept the H.B. Fuller General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, the total aggregate liability of H.B. Fuller for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or therwise, is limited to replacement of affected products or refund of the purchase price for affected products. H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses arising out of or in connection with product supply.

Nothing in any term shall operate to exclude or limit H.B. Fuller's liability for fraud, gross negligence or for death or personal injury caused by negligence or for breach of any mandatory implied terms.

Australia Tel: +61 1800 423 855 customer.service@hbfuller.com China & Hong Kong Tel: +86 20 82068291 cs.china@hbfuller.com Indonesia Tel: +62-21-5307232/33 Korea Tel: +82 2 786 8296 cskorea@hbfuller.com Malaysia Tel: +603 3345 5200 New Zealand Tel: +64 800 555 072 customer.service@hbfuller.com 
 Philippines

 Tel: +63 2 5194073

 Taiwan

 Tel: +886 2 26033385

 Thailand

 Tel: +66 2 3757442

 Vietnam

 Tel: +84 8 22225588





# **TECHNICAL DATA SHEET – OCTOBER 2017**

## **RAKOLL XL3 HV LOT**

### Limitations

Do not use RAKOLL XL3 HV LOT below 10°C. RAKOLL XL3 HV LOT is not suitable for exposed exterior or load bearing applications. If a faster setting or sandable cross-linking PVA is required, try RAKOLL XL3 PLUS. Lower viscosities can be obtained with RAKOLL XL3.

### Cleaning

Clean up adhesive while wet with warm water.

### Storage

Product should be stored in the original container out of direct sunlight between 5°C and 30°C and protected from freezing. Rotate stock using oldest batches first. Close containers air tight after use. For best performance use product within 12 months.

#### Safety & Disposal

This material is non-hazardous. Refer to the Material Safety Data Sheet (MSDS) for further information.

Page 2 of 2 Version 2 17/10/2017

### Made in Australia

### Our Focus is Clear. Perfecting Adhesives.

IMPORTANT: Information, specifications, procedures and recommendations provided ("information") are based on our experience and we believe this to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

NOTE TO USER: by ordering/receiving product you accept the H.B. Fuller General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, the total aggregate liability of H.B. Fuller for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or therwise, is limited to replacement of affected products or refund of the purchase price for affected products. H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses arising out of or in connection with product supply.

Nothing in any term shall operate to exclude or limit H.B. Fuller's liability for fraud, gross negligence or for death or personal injury caused by negligence or for breach of any mandatory implied terms.

Australia Tel: +61 1800 423 855 customer.service@hbfuller.com China & Hong Kong Tel: +86 20 82068291 cs.china@hbfuller.com Indonesia Tel: +62-21-5307232/33 Korea Tel: +82 2 786 8296 cskorea@hbfuller.com Malaysia Tel: +603 3345 5200 New Zealand Tel: +64 800 555 072 customer.service@hbfuller.com

 Philippines

 Tel: +63 2 5194073

 Taiwan

 Tel: +886 2 26033385

 Thailand

 Tel: +66 2 3757442

 Vietnam

 Tel: +84 8 22225588

