



## TECHNICAL DATA SHEET

Version 2  
01/02/2017

### FULLABOND 8911

- Type of Adhesive** FULLABOND 8911 is a pressure sensitive, vinyl acrylic emulsion copolymer exhibiting very aggressive wet and dry tack.
- Product Benefits** This adhesive has aggressive tack - even in low temperature applications. It has easy clean-up properties and excellent machining characteristics.
- Typical Applications** Major uses include bonding polyethylene and polypropylene films, polyolefin or wax-coated board for food packaging - including freezer packs - and any bonding application requiring very aggressive tack. Adhesion to polyethylene, polypropylene, Mylar and cellophane is excellent.

#### Typical Properties

Raw material base	Vinyl acrylic copolymer
Viscosity (Spindle 4, 60RPM, 25°C)	1,600 – 3,400 cP
Solids (%)	57 – 60
pH	4.5 – 5.5
Specific Gravity	0.97 – 1.03
Storage	Store out of direct sunlight between 10°C and 35°C. Protect from freezing. If freezing occurs the product will no longer be useable.
Shelf Life	For best results we recommend the product be used within six months
Clean-up	Clean up the adhesive while it's wet with warm soapy water
Safety	Please refer to SDS

**Made in Australia**

### Our Focus is Clear. Perfecting Adhesives.

IMPORTANT: Information, specifications, procedures and recommendations provided ("information") are based on our experience and we believe this to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

**NOTE TO USER:** by ordering/receiving product you accept the H.B. Fuller General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, the total aggregate liability of H.B. Fuller for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses arising out of or in connection with product supply.

Nothing in any term shall operate to exclude or limit H.B. Fuller's liability for fraud, gross negligence or for death or personal injury caused by negligence or for breach of any mandatory implied terms.

**Australia**  
Tel: +61 1800 423 855  
customer.service@hbfuller.com  
**China & Hong Kong**  
Tel: +86 20 82068291  
cs.china@hbfuller.com  
**Indonesia**  
Tel: +62-21-5307232/33

**Korea**  
Tel: +82 2 786 8296  
cskorea@hbfuller.com  
**Malaysia**  
Tel: +603 3345 5200  
**New Zealand**  
Tel: +64 800 555 072  
customer.service@hbfuller.com

**Philippines**  
Tel: +63 2 5194073  
**Taiwan**  
Tel: +886 2 26033385  
**Thailand**  
Tel: +66 2 3757442  
**Vietnam**  
Tel: +84 8 2225588



# H.B. Fuller