



### FULLAMELT 106

- Type of Adhesive** FULLAMELT 106 has been formulated as a low viscosity hot melt adhesive with excellent hot tack and aggressive adhesion properties temperatures through 24 to 48 hour cycles.
- Product Benefits** When fully cured, FULLAMELT 106 is suitable for indirect food contact applications.
- Typical Applications** FULLAMELT 106 is suitable for difficult to bond surfaces as well as use in blast and freezer carton sealing applications exposed to -40 to -45°C

#### Typical Properties

Raw material base	Synthetic polymer based hot melt
Colour	Light Straw
Viscosity at 175°C (Brookfield)	ca 600 cPs
Ring and Ball Softening Point	ca 105 °C
Application Temperature Range	160 - 180°C
Application Method	Nozzle, wheel, reservoir pump etc.
Shelf Life	12 months
FDA (Food and Drug Administration)	21 CFR 175.105 Adhesives
Safety Advice	Please refer to SDS

**Made in Australia**

### Our Focus is Clear. Perfecting Adhesives.

IMPORTANT: Information, specifications, procedures and recommendations provided ("information") are based on our experience and we believe this to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

**NOTE TO USER:** by ordering/receiving product you accept the H.B. Fuller General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, the total aggregate liability of H.B. Fuller for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses arising out of or in connection with product supply.

Nothing in any term shall operate to exclude or limit H.B. Fuller's liability for fraud, gross negligence or for death or personal injury caused by negligence or for breach of any mandatory implied terms.

**Australia**  
Tel: +61 1800 423 855  
customer.service@hbfuller.com  
**China & Hong Kong**  
Tel: +86 20 82068291  
cs.china@hbfuller.com  
**Indonesia**  
Tel: +62-21-5307232/33

**Korea**  
Tel: +82 2 786 8296  
cskorea@hbfuller.com  
**Malaysia**  
Tel: +603 3345 5200  
**New Zealand**  
Tel: +64 800 555 072  
customer.service@hbfuller.com

**Philippines**  
Tel: +63 2 5194073  
**Taiwan**  
Tel: +886 2 26033385  
**Thailand**  
Tel: +66 2 3757442  
**Vietnam**  
Tel: +84 8 2225588

