



TECHNICAL DATA SHEET

Version 1
01/02/2017

FULLAMELT 223

- Type of Adhesive** FULLAMELT 223 is a Hot Melt Spine Adhesive and exhibits a fast rate of set with excellent flexibility.
- Product Benefits** FULLAMELT 223 offers the user excellent adhesion and thermal stability, as well as heat resistance.
- Typical Applications** FULLAMELT 223 has been found particular useful where there is only a short delay after adhesive application before trimming takes place.

Typical Properties

Raw Material Base	Synthetic polymer based hot melt
Colour	White
Ring & Ball Softening Point	ca 100°C
Viscosity @ 177°C	2,800 - 3,200 cP
Application Temperature Range	170 – 180°C
Application Method	Extruder
Packaged Size	15 kg carton (pillows)
Shelf Life	1 year minimum
Safety Advice	Please refer to the SDS for safety advice.

Made in Australia

Our Focus is Clear. Perfecting Adhesives.

IMPORTANT: Information, specifications, procedures and recommendations provided ("information") are based on our experience and we believe this to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

NOTE TO USER: by ordering/receiving product you accept the H.B. Fuller General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, the total aggregate liability of H.B. Fuller for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses arising out of or in connection with product supply.

Nothing in any term shall operate to exclude or limit H.B. Fuller's liability for fraud, gross negligence or for death or personal injury caused by negligence or for breach of any mandatory implied terms.

Australia
Tel: +61 1800 423 855
customer.service@hbfuller.com
China & Hong Kong
Tel: +86 20 82068291
cs.china@hbfuller.com
Indonesia
Tel: +62-21-5307232/33

Korea
Tel: +82 2 786 8296
cskorea@hbfuller.com
Malaysia
Tel: +603 3345 5200
New Zealand
Tel: +64 800 555 072
customer.service@hbfuller.com

Philippines
Tel: +63 2 5194073
Taiwan
Tel: +886 2 26033385
Thailand
Tel: +66 2 3757442
Vietnam
Tel: +84 8 2225588



H.B. Fuller