



MAXBOND FLEXI-FLOOR

Maxbond Flexi-Floor timber flooring adhesive is a high strength, permanently flexible timber flooring adhesive specifically formulated for Australian conditions. Maxbond Flexi-Floor utilizes HB Fuller's PolyXSil Hybrid Enviro Technology™ and is designed for full-contact bonding of solid and engineered wood and cement sheet flooring installations to timber and cement-based sub-floors. Maxbond Flexi-Floor is also suitable for sub-flooring installations over both wood and steel joist flooring systems. Ready to use with no mixing required, Maxbond Flexi-Floor is extremely smooth and easy to trowel.

Maxbond Flexi-Floor cures by means of a chemical reaction initiated by atmospheric moisture. Once fully cured an elastic, acoustic and non-shrinkable adhesive layer is formed, which is resistant to moisture and heat. Maxbond Flexi-Floor has excellent adhesion to most common substrates used in the construction industry.

Maxbond Flexi-Floor carries a non-hazardous classification, is low in VOC and free from isocyanate. The formulation is free from water, silicone and solvents, thus minimizing the risk of deforming timber and affecting floor finishes.

Important note: Discrete from adhesive selection, Australian standard AS2870 requires a separate moisture vapor barrier membrane be applied to concrete sub-floors in all circumstances where concrete slabs contains a moisture content of greater than 5.5% (moisture meter) and the rate of water vapor transmission from the slab is greater than 15g/m² / 24 hrs (Calcium Chloride Test). In

most Australian regions the time to achieve this is normally at least 28 days.

Benefits

- Formulated to meet Australian Building Standards and Codes
- Elastomeric, permanently flexible with sound deadening/acoustic reduction properties
- Long open working time
- Contains no Water, Silicone, Solvents or Isocyanates
- No shrinking, gassing or foaming during curing
- Easy to apply, forms stable peaks once applied with a notched trowel
- Enhanced moisture control properties when applied with 6mm v-notch trowel (achieving 100% surface adhesive coverage.)
- Rapid Cure and Build-Up of bond strength – sandable after min. 24 hours.
- One part ready to use, no mixing required
- Easy to clean up
- Acoustic performance properties
- Resistant to temperature extremes: - 40°C to 90°C

Uses

- Elastic bonding many types of solid and engineered wood and cement based sub-floor and overlay flooring systems
- Suitable for porous and non-porous primary substrates
- Suitable for floors with underfloor heating – see refer installation notes

Our Focus is Clear. Perfecting Adhesives.

IMPORTANT: Information, specifications, procedures and recommendations provided ("information") are based on our experience and we believe this to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

NOTE TO USER: by ordering/receiving product you accept the H.B. Fuller General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, the total aggregate liability of H.B. Fuller for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses arising out of or in connection with product supply.

Nothing in any term shall operate to exclude or limit H.B. Fuller's liability for fraud, gross negligence or for death or personal injury caused by negligence or for breach of any mandatory implied terms.

Australia
Tel: +61 1800 423 855
customer.service@hbfuller.com
China & Hong Kong
Tel: +86 20 82068291
cs.china@hbfuller.com
Indonesia
Tel: +62-21-5307232/33

Korea
Tel: +82 2 786 8296
cskorea@hbfuller.com
Malaysia
Tel: +603 3345 5200
New Zealand
Tel: +64 800 555 072
customer.service@hbfuller.com

Philippines
Tel: +63 2 5194073
Taiwan
Tel: +886 2 26033385
Thailand
Tel: +66 2 3757442
Vietnam
Tel: +84 8 2225558

**H.B. Fuller**



Compatible Substrates

Concrete	Particleboard
Timber	Cementitious Screed*
MDF	Marble
Plywood	Porcelain Tiles
Steel Joists	Galvanised Steel
Bamboo**	SW Bamboo**
Stainless Steel	Compressed Cement Sheeting
Mild Steel	

*Contact HB Fuller Customer Service department for information on approved screeds.

**Maxbond Flexi-Floor compatibility with bamboo (including SW Bamboo) is dependent on the timber manufacture's installation guidelines. Do not use Maxbond Flexi-Floor where the timber manufacturer recommends against their boards being adhesively fixed.

Coverage

Trowel Size	Coverage per kg adhesive	Coverage per 15kg pail
4mm v notch	ca. 0.8-0.9m ²	ca. 12.5m ²
6mm v notch with 12mm centers	ca. 0.9m ²	ca. 12.6m ²

Performance Summary

Material Base	STP Polymer
Curing system	Moisture/Chemical Cure
Colour/Consistency	Tan paste
Specific Gravity	ca. 1.66
Solids content	100 %
Shore A Hardness	ca. 50
Modulus – 50%	ca. 1.3MPa
Modulus – 100%	ca. 1.8MPa
Shear Strength (DIN281b) wood/wood	>1 MPa
Coverage	ca. 12.5m ² per 15kg pail ca. 0.8-0.9m ² per 600ml sausage
Skin Time	60-80mins @ 23C
Repositioning Time	~4 hours @ 23C
Cure Rate	3-4mm/day @ 23C
Set to load bearing	Min 24 hours
Sanding / Finishing	Min 24 hours
Shelf Life	12 months unopened
Service Temperature	-40°C to 90°C

Under floor Heating

Maxbond Flexi-Floor is suitable for laying overlay flooring up to 20mm or parquet floor up to 25mm in thickness when used with underfloor heating systems. Use only stable species of timber when using parquet systems, IE species that will not be subject to significant expansion and contraction (see your flooring supplier for guidelines). When bonding parquet flooring the underfloor heating systems must have been operated for at least three weeks prior to laying to allow equilibration, even in summer this is required. Before laying parquet floor turn heating

Our Focus is Clear. Perfecting Adhesives.

IMPORTANT: Information, specifications, procedures and recommendations provided ("information") are based on our experience and we believe this to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

NOTE TO USER: by ordering/receiving product you accept the H.B. Fuller General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, the total aggregate liability of H.B. Fuller for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses arising out of or in connection with product supply.

Nothing in any term shall operate to exclude or limit H.B. Fuller's liability for fraud, gross negligence or for death or personal injury caused by negligence or for breach of any mandatory implied terms.

Australia
Tel: +61 1800 423 855
customer.service@hbfuller.com
China & Hong Kong
Tel: +86 20 82068291
cs.china@hbfuller.com
Indonesia
Tel: +62-21-5307232/33

Korea
Tel: +82 2 786 8296
cskorea@hbfuller.com
Malaysia
Tel: +603 3345 5200
New Zealand
Tel: +64 800 555 072
customer.service@hbfuller.com

Philippines
Tel: +63 2 5194073
Taiwan
Tel: +886 2 26033385
Thailand
Tel: +66 2 3757442
Vietnam
Tel: +84 8 2225588



system off for 48 hours prior to laying. If bonding parquet floor at low temperatures turn on heating system after bonding and allow to rise 5 °C every 24 hours. Maxbond Flexi-Floor can withstand heating up to 90°C.

Surface Preparation

Before applying Maxbond Flexi-Floor the subfloor substrate should be checked to ensure its suitability. All surfaces must be structurally sound before application. Where previous adhesives (PVA or bituminous adhesives) or contamination (waxes, coatings etc) is suspected or in evidence, thorough removal of all such contamination must be carried out. Concrete slabs should be built in accordance with Residential Footings and Slabs Code AS2870. Check the moisture content of the substrate with a carbide or electric hygrometer. The moisture content of the timber must be as recommended by the flooring manufacturer. In any case where the concrete slabs has a Moisture Content of greater than 5.5% (moisture meter) or in slab relative humidity exceeds 85% (hygrometer test), and the rate of water vapour transmission from the slab is greater than 15g/m²/24 hrs. (Calcium Chloride Test), apply Floorbond MCWB Vapor Barrier.

Substrate

Refer to Timber manufacturer's installation guides. Before installation of the timber / parquet, the substrate should be checked to ensure it is suitable. Check the moisture content throughout the entire thickness of the substrate with a carbide or electric hygrometer. The moisture content must be per Australian Building Standards codes & compliances and as recommended by the flooring manufacturer.

For fresh or new concrete and instances where moisture could be present in the concrete, Floorbond MCWB Vapor Barrier should be applied to the surface of the concrete prior to laying the flooring, as per directions. New concrete must be cured (per Australian Building Standards) until the moisture content of the slab is less than 5.5% (moisture meter) and the rate of water vapour transmission from the slab less than 15g/m²/24 hrs. (Calcium Chloride Test). The time to achieve this is normally at least 28 days.

The subfloor should be flat to 3mm over 3m. That is no gap more than 3mm beneath the straight edge when placed on the slab. If exceeding this, level the area with an approved cementitious screed (Refer to HBF Technical department). Using a 6mm trowel for 12-20mm overlay flooring will help fill low points however it is the responsibility of the floor layer to ensure that the timber makes good contact with the adhesive and a bonded surface area of at least 80% is achieved at all times.

When installing a parquet floor on top of marble, terrazzo or ceramic tiles they must be first cleaned with caustic soda or another suitable cleaner. Once cleaned, rinse the tiles thoroughly with plenty of clean water. Ensure the floor is completely dry before applying Maxbond Flexi-Floor.

Timber flooring

Refer to Timber manufacturer's installation guides. The timber flooring must be acclimatized for several days in the area where it is to be installed. Leave the timber in its original packaging until installation to avoid any deformation. Check before installation

Our Focus is Clear. Perfecting Adhesives.

IMPORTANT: Information, specifications, procedures and recommendations provided ("information") are based on our experience and we believe this to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

NOTE TO USER: by ordering/receiving product you accept the H.B. Fuller General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, the total aggregate liability of H.B. Fuller for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses arising out of or in connection with product supply.

Nothing in any term shall operate to exclude or limit H.B. Fuller's liability for fraud, gross negligence or for death or personal injury caused by negligence or for breach of any mandatory implied terms.

Australia
Tel: +61 1800 423 855
customer.service@hbfuller.com
China & Hong Kong
Tel: +86 20 82068291
cs.china@hbfuller.com
Indonesia
Tel: +62-21-5307232/33

Korea
Tel: +82 2 786 8296
cskorea@hbfuller.com
Malaysia
Tel: +603 3345 5200
New Zealand
Tel: +64 800 555 072
customer.service@hbfuller.com

Philippines
Tel: +63 2 5194073
Taiwan
Tel: +886 2 26033385
Thailand
Tel: +66 2 3757442
Vietnam
Tel: +84 8 2225558

**H.B. Fuller**



that the moisture content of the wood is as recommended by the supplier, (generally 9-14%). The correct humidity will depend upon the species of timber and the environment in which the timber will be laid. Higher humidity environments will generally use timber with higher humidity and the converse for dry environments.

Allow a gap of 1 to 1.5 cm around the perimeter of the laid timber flooring, including any columns or structures that penetrate the floor.

Applying the adhesive

Maxbond Flexi-Floor should be acclimatized to room temperature before installation. Temperature during application and cure should be between 10°C and 35°C*. Cure will be delayed at temperatures below 15°C. Apply the adhesive to the substrate by means of a suitable notched trowel (4mm v notch for small size parquetry, 6 mm v-notch with 12mm centres for boards). Do not apply more to the substrate than can be covered within 30 minutes. Slide the flooring onto the adhesive layer and tap into place or tamp down with a rubber hammer. Use enough pressure to ensure full constant contact between timber and adhesive. A minimum of 80% contact coverage is required to ensure adequate adhesion. Loading the flooring with weights will improve the final bond strength. Wait at least 24 hours before sanding and finishing the timber flooring.

*Note that in conditions of high temperature and humidity (>30°C & >50%RH), the skin and repositioning time of Maxbond Flexi-Floor is significantly reduced. In these conditions it is important to apply less Maxbond Flexi-Floor at a time, as the working time is reduced and the product will skin quicker than normal,

resulting in poor adhesion to the timber flooring.

Cure Time

Skin time 60-80 minutes, full bond set in 24-48 hours depending upon volume of adhesive used and climatic conditions. In warmer conditions and in conditions with high humidity (>30°C & >50%RH), the skin and repositioning time of Maxbond Flexi-Floor will be significantly reduced. Care should be taken in these conditions to ensure Maxbond Flexi-Floor does not skin prior to the timber flooring being applied, otherwise poor adhesion will result. It is recommended in high temperature and humidity conditions that the area that Maxbond Flexi-Floor is applied to is reduced to ensure adequate adhesive properties.

Clean Up

Uncured Maxbond Flexi-Floor may be removed from tools and substrates with a mild solvent e.g. methylated spirits, mineral turpentine, acetone. Cured adhesive must be removed mechanically, e.g. trimmed with a sharp knife.

Our Focus is Clear. Perfecting Adhesives.

IMPORTANT: Information, specifications, procedures and recommendations provided ("information") are based on our experience and we believe this to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

NOTE TO USER: by ordering/receiving product you accept the H.B. Fuller General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, the total aggregate liability of H.B. Fuller for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses arising out of or in connection with product supply.

Nothing in any term shall operate to exclude or limit H.B. Fuller's liability for fraud, gross negligence or for death or personal injury caused by negligence or for breach of any mandatory implied terms.

Australia
Tel: +61 1800 423 855
customer.service@hbfuller.com
China & Hong Kong
Tel: +86 20 82068291
cs.china@hbfuller.com
Indonesia
Tel: +62-21-5307232/33

Korea
Tel: +82 2 786 8296
cskorea@hbfuller.com
Malaysia
Tel: +603 3345 5200
New Zealand
Tel: +64 800 555 072
customer.service@hbfuller.com

Philippines
Tel: +63 2 5194073
Taiwan
Tel: +886 2 26033385
Thailand
Tel: +66 2 3757442
Vietnam
Tel: +84 8 2225558

**TECHNICAL DATA SHEET****技术资料****Shelf Life**

Maxbond Flexi-Floor will remain suitable for use for 12 months from date of manufacture if stored in original container in cool, dry place in temperatures < 30°C. Storage in high humidity or temperature will dramatically reduce the shelf life of this product.

Once opened, the remainder of a pail of Maxbond Flexi-Floor can be used for up to 6 weeks provided the following steps are taken:

1. Any cured material is removed from the pail
2. The foil disc is placed evenly on top of remaining product, ensuring it is sealed around all edges
3. The plastic lid is placed on top and pressed down securely
4. The pail is stored as per standard storage requirements IE cool, dry place with temperatures not exceeding 30°C.

Limitations

- Do not install to substrates that are not protected from rising damp
- Do not apply the adhesive at temperatures below 10°C or above 35°C*
- Do not apply the adhesive when the relative humidity is above 85%*
- Do not apply Maxbond Flexi-Floor on a dense burnished concrete surface without prior abrading or sanding back the surface to obtain mechanical key
- Do not install onto a substrate that contains too much moisture (refer Australian Building Standards) or onto substrates with a higher humidity value than recommended by the wood supplier.
- Do not install wood that is too dry (<9% humidity). This can expand at higher

humidity or when the humidity rises and cause damage

- Do not install if the walls and ceilings of the area are not dry (e.g. after plastering or painting etc.)
- Do not install on undulating concrete slabs.

Safety Information

This product is not considered hazardous under the classification of GHS WHS Version 8. Further safety information is available on the product SDS. Avoid contact with skin and eyes. Store in a dry place below 30°C. Keep out of reach of children. An MSDS is available from the H.B. Fuller representative in your state, HB Fuller Australia customer service, or downloadable from the HB Fuller web site, www.hbfuller.com.au

Disclaimer

This technical data sheet summarises at the date of issue to the best technical knowledge of HB Fuller Australia. Since HB Fuller Australia cannot anticipate or control the conditions under which the product may be used, each user must, prior to usage, review this technical data sheet in the context of how the user intends to handle and use the product in the workplace. If clarification or further information is needed to ensure that an appropriate assessment can be made, the user should contact this company. Our responsibility for the products sold is subject to our standard terms and conditions, a copy of which is sent to our customers and is also available on request

Version 5
TDS Date: 15/10/2025

Our Focus is Clear. Perfecting Adhesives.

IMPORTANT: Information, specifications, procedures and recommendations provided ("information") are based on our experience and we believe this to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

NOTE TO USER: by ordering/receiving product you accept the **H.B. Fuller General Terms and Conditions of Sale** applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, the total aggregate liability of H.B. Fuller for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses arising out of or in connection with product supply.

Nothing in any term shall operate to exclude or limit H.B. Fuller's liability for fraud, gross negligence or for death or personal injury caused by negligence or for breach of any mandatory implied terms.

Australia
Tel: +61 1800 423 855
customer.service@hbfuller.com
China & Hong Kong
Tel: +86 20 82068291
cs.china@hbfuller.com
Indonesia
Tel: +62-21-5307232/33

Korea
Tel: +82 2 786 8296
cskorea@hbfuller.com
Malaysia
Tel: +603 3345 5200
New Zealand
Tel: +64 800 555 072
customer.service@hbfuller.com

Philippines
Tel: +63 2 5194073
Taiwan
Tel: +886 2 26033385
Thailand
Tel: +66 2 3757442
Vietnam
Tel: +84 8 22225588